

# TECHNICAL DATA SHEET

## Pergo Svalbard

Edition

03.2016

# PERGO®

WOOD PARQUET

### General data

Panel	2200 x 220 mm		
Total thickness	14 mm		
Numbers of panels per pack	4		
m <sup>2</sup> per pack	1.936 m <sup>2</sup>		

### Panel build up

Toplayer	PEFC controlled sources	3.2 mm	
Core board	Spruce		
Backing layer	PEFC controlled sources	Spruce or Pine	1.35 mm
Tongue and groove	Length	Uniclic	
	Width	Perfect Fold 3.0 Connection	

### Surface layer

Wood species	Oak		
Origine	Europe		
Finishing	Matt lacquer / UV-hardening oil		

### Installation

Floating	On Pergo underlay	CF installation instructions
Glued to subfloor	Pergo MS polymere resin	CF installation instructions

### Warranty

Domestic use	Conditions in each pack	33 years
Uniclic connection	Lifetime	
Commercial	On request	

### Finishing

UV curing varnish	5 - 7 layers		
Wear resistance	SIS 923509	Falling sand	800 - 1000
	DIN 68861	S 33	100 - 1050
Scratch resistance	Anti-scratch top coat		
Stain resistance	EN 13442	All except blue ink	class 5
		Blue ink	class 3
CE	EN 14342: 2013	DOP PCO 0501	
Castor chairs	Use soft castors, type W (EN 12529) and/or suitable office mat		
Slip resistance	CEN/TS 15676	USRV 50-52	
Emission of formaldehyde	JIS A5108	F4 Star	
PCP	below detection limit		
Heat resistance	EN 12664	0.14 m <sup>2</sup> /KW	
Underfloor heating	Suitable	CF special installation instructions	
Reaction to fire	EN 14342	CWFT	Dfl-s1

### Ecological certificates

U-zeichen	Z.156.606-898
AFFSET	A
PEFC	PEFC/07-32-37
EPD	On request

