

# TECHNICAL DATA SHEET

## Pergo Värmdö

Edition

03.2016

# PERGO

WOOD PARQUET®

### General data

Panel	2200 x 190 mm
Total thickness	14 mm
Numbers of panels per pack	6
m <sup>2</sup> per pack	2,51 m <sup>2</sup>

### Panel build up

Toplayer	PEFC controlled sources	3,2 mm
Core board		Hevea
Backing layer	PEFC controlled sources	Spruce or Pine
Tongue and groove	Length	Uniclic
	Width	Uniclic

### Surface layer

Wood species	Oak/Iroko/Walnut/Merbau/Jatoba
Origine	Europe
Finishing	Matt / Satin lacquer

### Installation

Floating	On Pergo underlay	CF installation instructions
Glued to subfloor	Pergo MS polymere resin	CF installation instructions

### Warranty

Domestic use	Conditions in each pack	33 years
Uniclic connection		Lifetime
Commercial		On request

### Finishing

UV curing varnish		5 - 7 layers	
Wear resistance	SIS 923509	Falling sand	800 - 1000
	DIN 68861	S 33	100 - 1050
Scratch resistance		Anti-scratch top coat	
Stain resistance	EN 13442		All except blue ink class 5
			Blue ink class 3
CE	EN 14342: 2008-09		DOP PW 0501
Castor chairs		Use soft castors, type W (EN 12529) and/or suitable office mat	
Slip resistance	CEN/TS 15676		USRV 48-52
Emission of formaldehyde	EN 717-1		E1
PCP			below detection limit
Heat resistance	EN 12664		0,127 m <sup>2</sup> .KW
Underfloor heating	Suitable	CF special installation instructions	
Reaction to fire	EN 14342	CWFT	Dfl-s1
		With Oak toplayer	Cfl-s1

### Ecological certificates

U-zeichen	Z.156.606-898
AFFSET	A
PEFC	PEFC/07-32-37
M1	OK
EPD	On request

